



## DESCRIPTION

**EPL™ 9 is a slow set, self-leveling elastomer.**

## FEATURES

- 100% solids, no solvents, and zero VOCs.
- May be hand mixed, static mixer processed, or sprayed.
- Gel time 9 minutes at 77°F (25°C) approximately.
- Compliant with FDA/USDA for incidental food contact.

## RECOMMENDED USES

- Self-leveling base coat.
- Spot repair of pre-existing coatings.
- Deck repairs.
- Crack repairs.
- Hard to reach places not accessible to spray equipment.
- Control joint filler.
- Warehouse floor repairs.

## COLORS

EPL™ 9 is available in SPI standard Black. Note: In continuous full-light exposure, white or very light colors will yellow over a period of time. EPL™ 9 is available in a high-pigment, UV inhibited formulation for stand-alone applications, such as roofs and containment liners. Aliphatic urethane and other suitable topcoats can be used where long-term color stability and increased longevity in full sun exposure are of critical importance.

## PACKAGING

This product sold in standard 10, 30, 110 gallon drum and 550 gallon tote sets. Available in other container sizes, contact sales representative for further information. Non-standard containers may require a longer lead time.

## TYPICAL PHYSICAL PROPERTIES\*

<b>Service Temperature</b>	-50°F - +200° (-45°C - +93°C)
<b>Tensile Strength ASTM D638</b>	± 1,700 psi (12 MPa)
<b>Elongation ASTM D638</b>	± 350%
<b>Hardness (Shore A) ASTM D2240-81</b>	90 ± 5
<b>Hardness (Shore D) ASTM D2240-81</b>	40 ± 5
<b>100% Modulus ASTM D412</b>	800 psi (6 MPa) ± 5%
<b>300% Modulus ASTM D412</b>	1,580 psi (44 MPa) ± 5%
<b>Exposure Temperature**</b>	-50° - +200°F (-45° - 93°C)

## CURING SCHEDULE

<b>200 gram (100 A : 100 B) @ 77°F (25°C)</b>	
<b>Gel</b>	± 9 min.
<b>Tack Free</b>	± 1 hour
<b>***Final Cure</b>	24 hour
<b>Recoat</b>	0 - 12 hours

\* All cured film properties are approximate since processing parameters, ad-mixture types, and quantities change physical properties of the cured elastomer. Elevated temperatures will accelerate the curing process and shorten the re-coat window.

\*\* Test performed in a dry, static environment.

\*\*\* Complete polymerization to achieve final strength can take up to several days or weeks, depending on a variety of conditions or product type. All samples for above tests were force cured 48 hours or aged for more than three weeks. It is recommended that the user perform their own independent testing.

The samples for tests were sprayed with LPG equipment and Lock 'n Load gun. Test results from SPI.

## WET PROPERTIES

<b>Solids by Volume</b>	100%
<b>Solids by Weight</b>	100%
<b>Volatile Organic Compounds</b>	0 lbs/gal (0 g/l)
<b>Theoretical Coverage DFT</b>	100 sq. ft. @ 16 mils/gal
<b>Weight per gallon (approx.)</b>	8.88 lbs. (4.0 kg)
<b>Number of coats</b>	1 - 2
<b>Mix Ratio (by volume)</b>	1 "A" : 1 "B"
<b>Viscosity</b>	A: 450 ± 100 cps B: 600 ± 50 cps
<b>Shelf Life Unopened Containers @ 60 - 90°F (15 - 32°C)</b>	Six Months

Minimum material/container temperature for application is 70°F (21°C).

## GENERAL APPLICATION INSTRUCTIONS

Apply EPL™9 to only clean, dry, sound surfaces free of loose particles or other foreign matter.

A primer may be required; subject to type and condition of the substrate. Consult technical service for specific primer.

Read and observe all precautions, instructions, and limitations that are included with all containers of EPL™9.

EPL™9 is a "slow-set" (minutes) polyurea and may behave differently in the presence of moisture than "fast-set" (seconds) polyurea.

## LIMITATIONS

- This product is for professional use only.
- This product must be stored at temperatures between 60–90°F (15–32°C).
- Apply product when surface and air temperatures are above 40°F (5°C) and the surface temperature is at least 5°F (3°C) above dew point and rising.
- Liquid temperature in containers during application of product should be 70°F (21°C) minimum, 85°F (29°C) optimum, and 100°F (38°C) maximum.
- Product and hose temperature during application should be 85°F (29°C).
- Avoid moisture contamination in containers. Containers should not be released if contamination is suspected. CO<sub>2</sub> created pressure can develop. Do not attempt to use contaminated material.
- The material supplied is a two component system (Component "A"/Component "B"), which is used to formulate this product. The quality and characteristics of the finished polymer is determined by the mixture and application of the two components.
- Undried air exposed to liquid components will reduce physical properties of the cured coating.

For the most up to date technical data sheet and/or safety data sheet (SDS) visit our website at [specialty-products.com](http://specialty-products.com).

## RECOMMENDED EQUIPMENT SETTINGS

- Lock 'n Load™ gun with 12" mixer.
- Standard 1:1 ratio, LPG™ equipment developing a minimum of 50 - 500 psi (0.3 - 3.4 MPa)
- Substrate temperature should be a minimum of 50°F (10°C).

## GENERAL SAFETY, TOXICITY, & HEALTH

Safety Data Sheets are available for this coating material. Any individual who may come in contact with these products should read and understand the S.D.S. **CHEMTREC EMERGENCY NUMBER 1-800-424-9300**

**WARNING:** Contact with skin or inhalation of vapors may cause an allergic reaction. Causes eye damage/irritation. Avoid eye contact with liquid or spray mist. Hypersensitive persons should wear protective clothes, gloves and use protective cream on face, hands and other exposed areas.

**CONTAMINATION:** Avoid moisture contamination in containers. Containers should not be resealed if contamination is suspected, carbon dioxide created pressure can develop. Do not attempt to use contaminated material.

**EYE PROTECTION:** Safety eye wear complying with an approved standard should be used when a risk assessment indicates this is necessary to avoid exposure to liquid splashes, mists, or dusts. If contact is possible, the following protection should be worn, unless the assessment indicates a higher degree of protection: chemical splash goggles and/or face shield.

**SKIN PROTECTION:** Personal protective equipment for the body should be selected based on the task being performed; the risks involved, and should be approved by an industrial hygiene specialist before handling this product. Chemical resistant gloves are recommended. Cover as much of the exposed skin area as possible with appropriate clothing.

**RESPIRATORY PROTECTION:** Harmful if inhaled and may cause allergy or asthma symptoms. Ensure adequate ventilation. If the respirator is the sole means of protection, use a full-face supplied respirator. Use respirators and components tested and approved under appropriate government standards such as OSHA 29CFR 1910.134, NIOSH (US), or CEN (EU). Consider the application and environmental concentrations when deciding if additional protective measures are necessary.

**INGESTION:** Do not take internally. It is believed that ingestion of polymeric isocyanates would not be fatal to humans, but may cause inflammation of mouth and stomach tissue.

## WARRANTY & DISCLAIMER

Specialty Products, Inc. has no role in the manufacture of the finished polymer other than to supply its two components. It is vital that the person applying this product understands the product, and is fully trained and certified in the use of plural-component equipment. Specialty Products, Inc., an Alaska corporation, warrants only that the two components of this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product are dependent upon the proper mixture and application of the components by the applicator. There are no warranties that extend beyond the description on the face of this instrument. Failure to apply the product within the parameters stated on this document shall void the warranty. SPECIALTY PRODUCTS, INC. MAKES NO WARRANTY OF MERCHANTABILITY OF THE PRODUCT OR OF FITNESS OF THE PRODUCT FOR ANY PARTICULAR PURPOSE. Specialty Products, Inc. makes no warranty as to the quality of any product modified, supplemented, tinted, or altered in any way after it leaves the manufacturing plant. Specialty Products, Inc. does not warrant that this product is suitable for use as a liner for potable water containers. Use of this product in a potable water container could be hazardous to health if it is improperly processed or applied. The liability of Specialty Products, Inc. for any nonconformity of the product to its technical specifications shall be limited to replacement of the product. The sole exclusive remedy of buyer, which is to have Specialty Products, Inc. replace any nonconforming product at no cost to buyer, is under the condition that the buyer notifies Specialty Products, Inc. or its distributor in writing of such defect within thirty days of the discovery of such defect. Specialty Products, Inc. shall not be liable for any direct, incidental, or consequential damages resulting from any breach of warranty.

The data presented herein is intended for professional applicators or those persons who purchase or utilize this product in the normal course of their business. The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer. The aforementioned data on this product is to be used as a guide and is subject to change without notice. The information herein is believed to be reliable, but unknown risks may be present. Specialty Products, Inc. makes no warranties, expressed or implied, including patent warranties or warranties of merchantability or fitness of use, with respect to products or information set forth herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent. Accordingly, the buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Specialty Products, Inc. of all liability with respect to the materials and the use thereof.



**SPI The Single Source Solution Since 1974**  
**Serving the Plural-Component Industry**

**Product & Equipment Technical Assistance**  
**24 hours - 7 days a week 800 627 0773**



**SPI Website**

**CONTACT US**

2410 104<sup>th</sup> St. Ct. S. Suite D, Lakewood, WA 98499  
**SPECIALTY-PRODUCTS.COM**  
1 800 627 0773 **FAX 253 588 7196**  
info@specialty-products.com



**SPI Media**



**"Proudly Manufactured in the USA"**