

DESCRIPTION

ULTRA BOND™ 100 is a high tensile, high elongation, high build, fast-set elastomer, specifically formulated to provide a tenacious bond to certain thermoset plastic surfaces. Unlike most spray-applied polyureas, SPI's advanced Ultra Bond™ 100 chemistry is coined "the duct tape molecule". Ultra Bond™ 100 has the unique advantage of adhering to most properly prepared organic and inorganic (new and aged) surfaces without requiring a primer. Like duct tape, ULTRA BOND™ 100 gains adhesion over time.

FEATURES

In house testing has shown excellent adhesion to certain clean dry surfaces including:

- Primers past the re-coat window
- Latex rubber
- Crumb rubber surfaces
- Melamine
- Firestone SBS roofing membrane
- Epoxy
- SBR rubber
- Aged polyurea
- Automotive finishes
- Roofing
- Glass
- Sarnafil vinyl roofing membrane
- Line-x bed liner.

RECOMMENDED USES

- Coating over organic primers that are past their re-coat window. These include SPI POLYPRIME™ 100 and EP™ 100.
- Repair of polyurea liners.
- For texturing aged polyurea.
- Top coat compatible existing membrane liners
- Re-coat urethane liners.
- Re-coat over other polymer based substrates used for flooring, wall covering, and infrastructure protection.

COLORS

ULTRA BOND™ 100 is available in SPI standard colors (Sand, Medium Grey, and Black). Custom colors available upon request. Note: ULTRA BOND™ 100 is an aromatic polyurea. Therefore, with all aromatics, color change and superficial oxidation will occur. Aliphatic urethane and other suitable topcoats can be used where long-term color stability and increased longevity in full sun exposure are of critical importance.

PACKAGING

This product sold in standard 110 gallon drum and 550 gallon tote sets. Available in other container sizes, contact sales representative for further information. Non-standard containers may require a longer lead time.

TYPICAL PHYSICAL PROPERTIES*

Tensile Strength ASTM D412	± 3,000 psi (20.85 MPa)
Elongation ASTM D412	± 450%
Hardness (Shore A) ASTM D2240	85 ± 5
Hardness (Shore D) ASTM D2240-81	42 ± 5
100% Modulus ASTM D412	680 psi (4.7 MPa) ± 5%
Tear Resistance ASTM D624	380 PLI (66.54 KN/M) ± 50
Exposure Temperature**	-50° - +200°F (-45° - +93°C)

CURING SCHEDULE

Gel	± 12 sec
Tack Free	± 30 sec
Post Cure***	24 hours
Recoat	0 min - 12 hours

* All cured film properties are approximate since processing parameters, ad-mixture types, and quantities change physical properties of the cured elastomer. Elevated temperatures will accelerate the curing process and shorten the re-coat window.

** Test performed in a dry, static environment.

*** Complete polymerization to achieve final strength can take up to several days or weeks, depending on a variety of conditions or product type. All samples for above tests were force cured 48 hours or aged for more than three weeks. **It is recommended that the user perform their own independent testing.**

The samples for tests were sprayed with Graco HXP3 @ 2,500 psi 17.3 MPa dynamic pressure at the gun. Proportioning machine primary heater and hose heat 170°F (77°C) Graco MP Fusion gun with 29/29 mixing chamber with .040 ceramtip.

WET PROPERTIES

Solids by Volume	100%
Solids by Weight	100%
Volatile Organic Compounds	0 lbs/gal (0 g/l)
Theoretical Coverage DFT	100 sq. ft. @ 16 mils/gal
Weight per gallon (approx)	8.8 lbs. (4.00 kg)
Number of coats	1 - 2
Mix Ratio	1 "A" : 1 "B"
Viscosity @77°F (25°C)	A: 750 ± 100 cps B: 300 ± 25 cps
Shelf Life Unopened Containers @ 60 - 90°F (15 - 32°C)	Six Months

Minimum material/container temperature for application is 70°F (21°C).

MIXING & THINNING

Thoroughly agitate the "B" components of this product prior to application. Use a SPI folding blade mixer, or equivalent equipment approved by SPI. Install mixer through the extra air specific 2" bung hole provided on all "B" drums. Care must be taken not to cross contaminate the individual components with the mixing equipment; for best mixing results, supply the SPI mixer with 25 cfm of air at 100 psi. Thinning is not required. Using any thinner may adversely affect product performance.

GENERAL APPLICATION INSTRUCTIONS

Apply ULTRA BOND™ 100 only to clean, dry, sound, surfaces free of loose particles or other foreign matter. ULTRA BOND™ 100 can be sprayed over a broad range of ambient and substrate temperatures. It is recommended that ULTRA BOND™ 100 be sprayed in multi-directional (north/south - east/west) passes to ensure uniform thickness.

Contact SPI technical service personnel for specific surface preparation for your application.

COMMON SUBSTRATES:

STEEL: 4-5 mil anchor profile is best for maximum adhesion and varies per application and conditions; adhere to proper SSPC standards.

WOOD: Apply polyurea onto a clean, dry, and sanded surface; free from burrs, splinters and loose debris. (It is recommended to prime wood and other porous surfaces before application of heated, fast-set polyureas to reduce pin holing).

CONCRETE: Prepare concrete in accordance with SSPC/NACE Standards and SPI Concrete Prep Guide.

PREVIOUSLY APPLIED COATINGS: SPI recommends UB™ (ULTRA BOND™) products over existing coatings that are past the recoat window and/or application over other coatings. Contact SPI for additional information.

NOTE: It is recommended that existing surfaces be power washed with 2500—3500 psi water pressure to enhance adhesion of ULTRA BOND™ 100. If there is a possibility of surface contamination, scrub with a solution of 1/4 tsp Dawn

detergent and 1 tbsp of vinegar, per 1 gallon of warm water. Follow with a thorough water rinse. If there is oxidation on the surface of the existing substrate; it must be removed prior to application of ULTRA BOND™ 100. Removal of oxidation can be done via mechanical methods to insure the ULTRA BOND™ 100 has a sound substrate to adhere to. The use of SPI Prep Wipe™ solution will tack up the existing polyurea coating and help promote bonding of the ULTRA BOND™ 100.

On all above listed substrates and others, please contact SPI Sales or Technical Support for more information specific to your application, including industry standards such as SSPC and NACE. **Adhesion tests are always recommended prior to application.**

PROCESSING EQUIPMENT & SETTINGS

MACHINES:

GRACO (Gusmer, Glass-craft)	<ul style="list-style-type: none"> • A-25* • A-XP1 • E-10 HP • E-20* • E-30* • E-XP1 • E-XP2 • H-20/35 Pro • H-25* • H3500 • H-40* 	<ul style="list-style-type: none"> • H-50* • HV-20/35 • H-XP2 • H-XP3 • Reactor2 E-XP2 • Reactor2 H-XP2 • Reactor2 H-XP3 • Reactor2 E-30* • Reactor2 H-30* • Reactor2 H-40* • Reactor2 H-50*
PMC	<ul style="list-style-type: none"> • GH-25* • GH-40* • PA-25* • PAX-25 • PH-2* • PH-25* 	<ul style="list-style-type: none"> • PH-40* • PHX-2 • PHX-25 • PHX-40 • PMCA-20
SPRAY FOAM EQUIP & MFG	<ul style="list-style-type: none"> • 5/12K* • 6/6K* 	<ul style="list-style-type: none"> • 6/12K

*2,000 psi machines

GUNS:

GRACO (Gusmer, Glass-craft)	<ul style="list-style-type: none"> • Fusion AP • Fusion MP • GAP Pro • GX7-DI • GX-8 Pro 	<ul style="list-style-type: none"> • GX7-400 • P2 • P2 Elite • P2 Elite "C" • D7
PMC	<ul style="list-style-type: none"> • AP-2 	
SPRAY FOAM EQUIP & MFG	<ul style="list-style-type: none"> • Boss 	

- Standard 1:1 ratio, heated, plural-component equipment developing a minimum of 2000 psi (10.4 MPa) dynamic pressure at the gun with heating capabilities to 170°F (77°C) will adequately spray ULTRA BOND™ 100.
- Machines capable of producing a higher dynamic psi may be required depending on the service environment the ULTRA BOND™ 100 will be exposed to. Consult SPI technical service personnel for additional information.
- Proportioning machine primary heater temperature 160-170°F (71-77°C)
- Hose temperature 160-170°F (71-77°C). A hose thermometer inserted under the insulation near the gun

should read a minimum of 145-155°F (63-68°C).

- Physical properties will be enhanced when sprayed at higher pressure (3000 psi or more); utilizing an impingement mix gun such as MP Fusion or GX7-DI gun.
- Do not use mixing chambers with output greater than 1.5 gallons per minute. Consult SPI technical service personnel for additional information.

If you own a machine that is not listed above please contact your SPI representative for information and instructions.

PARAMETERS & LIMITATIONS

- ULTRA BOND™ 100 is for professional use only. User must be proficient in the application of ULTRA BOND™ 100 and the use of the high pressure heated plural component equipment used to apply it.
- ULTRA BOND™ 100 must be stored at temperatures between 60–90°F (15–32°C).
- Liquid temperature in containers/drums during application 70–100°F (21–38°C).
- Apply ULTRA BOND™ 100 when surface and air temperatures are above 40°F (5°C) and the surface temperature is at least 5°F (3°C) above dew point and rising.
- Avoid moisture contamination in containers. Containers should not be resealed if contamination is suspected. CO₂ created pressure can develop. Do not attempt to use contaminated material.
- Undried air exposed to liquid components will reduce physical properties of the cured coating.

Note: The material supplied is a two component system (component “A”/component “B”), which is used to formulate this product. The quality and characteristics of the finished polymer is determined by the mixture and application of the two components by the person applying polymers.

For the most up to date technical data sheet and/or safety data sheet visit our website at www.specialty-products.com.

GENERAL SAFETY, TOXICITY, & HEALTH

Safety Data Sheets are available for this coating material. Any individual who may come in contact with these products should read and understand the S.D.S. **CHEMTREC EMERGENCY NUMBER 1-800-424-9300**

WARNING: Contact with skin or inhalation of vapors may cause an allergic reaction. Avoid eye contact with the liquid or spray mist. Hypersensitive persons should wear protective clothes, gloves and use protective cream on face, hands and exposed areas.

CONTAMINATION: Avoid moisture contamination in containers. Containers should not be resealed if contamination is suspected. CO₂ created pressure can develop. Do not attempt to use contaminated material.

CLEAN UP: Use DPM, NMP, and Polyclean.

EYE PROTECTION: Safety eye wear complying with an

approved standard should be used when a risk assessment indicates this is necessary to avoid exposure to liquid splashes, mists, or dusts. If contact is possible, the following protection should be worn, unless the assessment indicates a higher degree of protection: chemical splash goggles and/or face shield.

SKIN PROTECTION: Personal protective equipment for the body should be selected based on the task being performed; the risks involved, and should be approved by an industrial hygiene specialist before handling this product. Chemical resistant gloves are recommended. Cover as much of the exposed skin area as possible with appropriate clothing.

RESPIRATORY PROTECTION: Harmful if inhaled and may cause allergy or asthma symptoms. Use a respirator approved for isocyanates and organic vapors. If you are not sure, or not able to monitor levels, or if you are spraying in an enclosed/indoor area, use MSHA/NIOSH approved supplied air respirator. Consider the application and environmental concentrations when deciding if additional protective measures are necessary.

INGESTION: Do not take internally. It is believed that ingestion of polymeric isocyanates would not be fatal to humans, but may cause inflammation of mouth and stomach tissue.



SEAMLESS SOLUTIONS FOR OVER 40 YEARS



WARRANTY & DISCLAIMER

Specialty Products, Inc. has no role in the manufacture of the finished polymer other than to supply its two components. It is vital that the person applying this product understands the product, and is fully trained and certified in the use of plural-component equipment. Specialty Products, Inc., an Alaska corporation, warrants only that the two components of this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product are dependent upon the proper mixture and application of the components by the applicator. There are no warranties that extend beyond the description on the face of this instrument. Failure to apply the product within the parameters stated on this document shall void the warranty. SPECIALTY PRODUCTS, INC. MAKES NO WARRANTY OF MERCHANTABILITY OF THE PRODUCT OR OF FITNESS OF THE PRODUCT FOR ANY PARTICULAR PURPOSE. Specialty Products, Inc. makes no warranty as to the quality of any product modified, supplemented, tinted, or altered in any way after it leaves the manufacturing plant. Specialty Products, Inc. does not warrant that this product is suitable for use as a liner for potable water containers. Use of this product in a potable water container could be hazardous to health if it is improperly processed or applied. The liability of Specialty Products, Inc. for any nonconformity of the product to its technical specifications shall be limited to replacement of the product. The sole exclusive remedy of buyer, which is to have Specialty Products, Inc. replace any nonconforming product at no cost to buyer, is conditioned upon buyer notifying Specialty Products, Inc. or its distributor in writing of such defect within thirty days of the discovery of such defect. Specialty Products, Inc. shall not be liable for any direct, incidental, or consequential damages resulting from any breach of warranty. The data presented herein is intended for professional applicators or those persons who purchase or utilize this product in the normal course of their business. The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer. The aforementioned data on this product is to be used as a guide and is subject to change without notice. The information herein is believed to be reliable, but unknown risks may be present. Specialty Products, Inc. makes no warranties, expressed or implied, including patent warranties or warranties of merchantability or fitness of use, with respect to products or information set forth herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent. Accordingly, the buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Specialty Products, Inc. of all liability with respect to the materials and the use thereof.

SPI The Single Source Solution Since 1974
Serving the Plural-Component Industry

Product & Equipment Technical Assistance
24 hours - 7 days a week 800 627 0773



SPI Website

CONTACT US

2410 104th St. Ct. S. Ste D, Lakewood, WA 98499
SPECIALTY-PRODUCTS.COM
1 800 627 0773 FAX 253 588 7196
info@specialty-products.com



SPI Media



"Proudly Manufactured in the USA"